



Aqua




Fiesta




Latte



Navy




Platinum




Riveria



Sunburst



Tango



Volcano



Willow

TRADEWINDS (Tradewinds 'SOL'utions Collection)

Specifications

Usage	General Domestic Indoor/Outdoor/Draperies
Composition	100% Polyester Solution Dyed
Pattern Repeat	V:53cm x H:31cm
Width	140cm
Railroaded	No
Care Label	SOL F/4
Swish	Yes
Water Resistant	Yes
Metres on roll (approx.)	35 metres
Price Code	Green

Test Results

Abrasion resistance - Martindale (ISO 12947)	18,000 cycles
Abrasion resistance - Wyzenbeek (ASTM D3597)	7,500 cycles
Seam slippage (ISO 13936-2, Load 180)	Warp: 5.8mm, Weft: 5.0mm
Pilling resistance (ISO 12945-2)	5
Colourfastness to light (ISO 105-B02, blue std 6)	Greater than 7
Colourfastness to dry cleaning (ISO 105-D01:1993)	Colour change: 5, Staining solvent: 5
Colourfastness to water (ISO 105-E01)	Colour change: 5, Staining multifibre: 5, Self: 5

Fabric may vary in colour due to the nature of the media



131 Metrolink Circuit
Campbellfield, Victoria 3061
+61 9357 8807
sales@profilefabrics.com.au
www.profilefabrics.com.au
www.swishworldfabrics.com.au



TRADEWINDS (Tradewinds 'SOL'utions Collection)

Test Results

Colourfastness to shampoo (AS2111.19.2)	Colour change: 5, Staining Multifibre: 5, Self: 5
Colourfastness to rubbing (ISO 105-X12)	Dry: 5, Wet: 5
Colourfastness to perspiration, alkaline (ISO 105-E04)	Colour change: 5, Staining Multifibre: 5, Self: 5
Colourfastness to washing (ISO 105-C06, B1S)	Colour change: 5, Staining Multifibre: 5, Self: 5
Colourfastness to sea water (ISO 105-E02)	Colour change: 5, Staining Multifibre: 5, Self: 5
Colourfastness to chlorinated water (ISO 105-E03m 50mg/L)	Colour change: 5
Dimensional change - laundering (ISO 6330.7BA)	Dimensional chg (%) Warp: -0.1, Weft: -0.1
Dimensional change due to hanging (AS2663.1.B-1997)	Dimensional chg (%) Warp: 0.0, Weft: 0.0
Free and hydrolysed formaldehyde (ISO 14184-1:1998)	Not detectable
Colour change after bleaching and hot water extraction	Colour change: 5