



Viva Blue Steel



Viva Graphite



Viva Mushroom




Viva Oatmeal




Viva Obsidian



Viva Pebble




Viva Polar



Viva Sambar



Viva Steam



Viva Storm

## VIVA

### Specifications

Usage	Heavy Commercial
Composition	56% Polyurethane, 44% Nylon
Pattern Repeat	Plain
Width	137cm
Railroaded	Yes
Care Label	Viva Faux Leather PU
Swish	No
Metres on roll (approx.)	26 metres
Price Code	Green
Fire Rated AS1530.3 Tested	Yes

### Test Results

Abrasion resistance - Martindale (ISO 12947)	100,000 cycles
Colourfastness to water (AS 2001.4.E01-2001)	Colour change, Staining of Nylon/Cotton: 4-5
Colourfastness to perspiration (AS 2001.4.E01-2005)	Colour change, Staining of Nylon/Cotton: 4-5
Colourfastness to light (ISO 105-B02, blue std 6)	Greater than 6
Colourfastness to rubbing (AS 2001.4.3-1995)	Dry: 4-5, Wet: 4-5
Colourfastness to chlorinated swimming pool water	Colour change: 4-5
Tensile strength & elongation at break (BS 3144.5-1968)	Length: 58.2kg/cm <sup>2</sup> , Width: 67.1kg/cm <sup>2</sup>

Fabric may vary in colour due to the nature of the media

## Fire Rating AS1530.3 Results

Ignition Time	Standard Error: 0.16, Mean: 9.59 min
Flame Propagation Time	Standard Error: Nil, Mean: Nil sec
Heat Release Integral	Standard Error: 4.1, Mean: 86.6 kJ/m <sup>2</sup>
Smoke Release, log d	Standard Error: 0.0424, Mean: -1.3326
Optical Density, d	Mean: 0.0477 / Metre
Number of Specimens Tested and Ignited	6

### Regulatory Indices:

Ignitability Index	10 (Range 0-20)
Spread of Flame Index	0 (Range 0-10)
Heat Evolved Index	3 (Range 0-10)
Smoke Developed Index	3 (Range 0-10)